



Material - AFNOR NF 50 CD 4-M

Standard Specification for Cast Steels and White Cast Iron Resistant to Abrasion

Group - Ferrous Mild Steel Alloys

Sub Group - AFNOR NF 50 CD 4-M Cast Steels and White Cast Iron Resistant to Abrasion

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.460 - 0.540	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.800 - 1.200		
Molybdenum	Mo %	0.150 - 0.350		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	500 - 650
-	-	-	Elongation in %	5 - 12
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	220 - 330
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1606.0000	SS	Sweden	Casting
1050	AISI	USA	Forging, Bar, Wire, and Shape
5152	SAE	USA	Steel
735 A 51	BS	British	Hot Formed Spring
C 3	MSZ	Hungary	Steel
C48GW-N-A	JIS	Japan	Forging
A732 4A	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.