



Material - AFNOR NF A 420 C-M

Standard Specification for Steel Casting and Nickel Alloy Castings for Pump, Valve and Fitting

Group - Ferrous Mild Steel Alloys

Sub Group - AFNOR NF A 420 C-M Steel Casting and Nickel Alloy Castings for Pump, Valve and Fitting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Pump, Valve and Fitting

Chemical Composition			Heat Treatment	
Carbon	C %	0.230 max.	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 420 min. Yield Strength in Mpa 240 min. Elongation in % 25 min. Reduction of Area in % - Hardness in HB 130 - 165 Impact in Joule 24 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 GP240GH	BS	British	Plate, Tubes and Forging
A 216 Grade WCB	ASTM	USA	Casting
A 420 M	AFNOR NF	France	Pump, Valve and Fitting
Ao 17 CrMoV	MSZ	Hungary	Plate, Tubes and Forging
SCPH 1	JIS	Japan	Plate, Tubes and Forging
GP 240 GH	UNE	Spain	Plate, Tubes and Forging
1.0619	EN	European Union	Plate, Tubes and Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.