



Material - AFNOR NF G24Mn6

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - AFNOR NF G24Mn6 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.250		
Silicon	Si %	0.600 max.	Normalizing or Quenching or Solution Annealing	
Manganese	Mn %	1.500 - 1.800		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	0.300 max.		
Molybdenum	Mo %	0.150 max.		
Nickel	Ni %	0.400 max.		
Copper	Cu %	0.300 max.	Mechanical Properties	
Vanadium	V %	0.050 max.	Tensile Strength in Mpa	600 - 800
Iron	Fe %	Balance	Yield Strength in Mpa	400 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-		Impac <mark>t in Joule</mark>	27 J @ RT

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
EN 10213 G24Mn6	BS	British	Plate, Tubes and Forging		
G24Mn6	EN	European Union	Casting		
G24Mn6	DIN	Germany	Casting		
G24Mn6	UNI	Italy	Casting		
G24Mn6	PN	Poland	Casting		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.