



Material - AFNOR NF P 1000 - 30CrNiMo8

Standard Specification for Mild Steel Alloys Bar and Rod

Group - Ferrous Mild Steel Alloys

Sub Group - AFNOR NF P 1000 - 30CrNiMo8 Mild Steel Alloys Bar and Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.260 - 0.340	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	1.800 - 2.200		
Molybdenum	Mo %	0.300 - 0.500		
Nickel	Ni %	1.800 - 2.200		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 1000 - 1150 Yield Strength in Mpa 770 min. Elongation in % 10 min. Reduction of Area in % - Hardness in BHN 280 min. Impact in Joule 30 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
30CrNiMo8	EN	European Union	Bar and Rod
1.658	EN	European Union	Bar and Rod
30 CND 8	AFNOR NF	France	Bar and Rod
NCMo 6 Z	MSZ	Hungary	Bar and Rod
NCMo 6	MSZ	Hungary	Bar and Rod
30CrNiMo8	ISO	International	Bar and Rod
31 CrNiMo 8	ISO	International	Bar and Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.