



## Material - AFNOR NF P355Q

### Standard Specification for Flat Products Made of Steels for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - AFNOR NF P355Q Flat Products Made of Steels for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.160 max.	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	0.300 max.		
Nickel	Ni %	0.500 max.		
Molybdenum	Mo %	0.250 max.		
Vanadium	V %	0.060 max.		
Titanium	Ti %	0.030 max.		
Niobium	Nb %	0.050 max.	Mechanical Properties	
Zirconium	Zr %	0.050 max.	Tensile Strength in Mpa	490 - 630
Boron	B %	0.005 max.	Yield Strength in Mpa	315 min.
Nitrogen	N %	0.015 max.	Elongation in %	22 min.
Iron	Fe %	Balance	Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	40 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.8830	EN	European Union	Steel
1.8866	DIN	Germany	Steel
C450L0	AS	Australia	Steel
4020	AISI	USA	Forging, Bar, Wire, and Shape
P355QH	UNI	Italy	Steel
C450	AS	Australia	Steel
A732 6N	ASTM	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.