



Material - AFNOR NF X1CrNi25-21

Standard Specification for Seemless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - AFNOR NF X1CrNi25-21 Seemless Steel Tubes for Pressure Purposes
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.	Solution Annealing	
Silicon	Si %	0.250 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	24.000 - 26.000		
Molybdenum	Mo %	0.200 max.		
Nickel	Ni %	20.000 - 22.000		_
Nitrogen	N %	0.110 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	470 - 2100
-	-	-	Yield Strength in Mpa	180 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	220 max.
-	-	-	Impac <mark>t in Joule</mark>	60 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1.4335	EN	European Union	Tube	
1.4335	DIN	Germany	Steel	
1.4335	DIN	Germany	Steel	
X1CrNi25 21	DIN	Germany	Steel, Rolling and Forging	
X1CrNi25 21	UNI	Italy	Steel, Sheet, Strip and Plate	
X1CrNi25-20	AFNOR NF	France	Steel and Tube	
Z1CN25-20	AFNOR NF	France	Steel and Tube	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.