



Material - AFNOR NF X1CrNiMoCuN20-18-7

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - AFNOR NF X1CrNiMoCuN20-18-7 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.	Solution Annealing	
Silicon	Si %	0.700 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.010 max.		
Chromium	Cr %	19.500 - 20.500		
Molybdenum	Mo %	6.000 - 7.000		
Nickel	Ni %	17.500 - 18.500		
Copper	Cu %	0.500 - 1.000		
Nitrogen	N %	0.180 - 0.250		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 500 - 2100 Yield Strength in Mpa 300 min. Elongation in % 20 min. Reduction of Area in % - Hardness in BHN 260 max. Impact in Joule 60 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
0216-5 EN 1.4547	BS	British	Tube
1.4547	DIN	Germany	Steel, Bar and Rod
1.4547	EN	European Union	Steel, Bar and Rod
X1CrNiMoCuN20-18-7	UNI	Italy	Steel, Sheet, Strip and Plate
X1CrNiMoCuN20-18-7	DIN	Germany	Steel, Sheet, Strip and Plate
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.