



## Material - AFNOR NF X3CrNiN18-10

## Standard Specification for Seemless Steel Tubes for Pressure Purposes

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - AFNOR NF X3CrNiN18-10 Seemless Steel Tubes for Pressure Purposes
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Steel and Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 max.	Solution Annealing	
Silicon	Si %	0.750 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	17.000 - 19.000		
Nickel	Ni %	9.000 - 11.000		
Nitrogen	N %	0.120 - 0.200		_
Iron	Fe %	Balance	Mechanical Properties	
-	<b>—</b>		Tensile Strength in Mpa	570 - 770
-	-	-	Yield Strength in Mpa	270 min.
-	-	-	Elongation in %	40 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in BH</mark> N	-
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1.4311	EN	European Union	Tube	
1.4311	DIN	Germany	Steel	
1.4311	DIN	Germany	Steel	
CrNi18/9-0.03C/N	BS	British	Steel and Flat	
SUS 304 LN	JIS	Japan	Steel, Plate, Sheet and Strip	
X20CrNiN 18-10	UNI	Italy	Sheet, Plate, Strip and Bar	
X2CrNiN18 10 KKW	ONORM	Australia	Steel	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.