



Material - AFNOR NF X6CrNiMoNb17-12-2

Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - AFNOR NF X6CrNiMoNb17-12-2 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Bar and Rods

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	16.500 - 18.500		
Molybdenum	Mo %	2.000 - 2.500		
Nickel	Ni %	10.500 - 13.500		
Niobium	Nb %	1.000 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 510 - 740 Yield Strength in Mpa 215 min. Elongation in % 30 min. Reduction of Area in % - Hardness in HB 230 max. Impact in Joule 60 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4580	EN	European Union	Tube
1.458	DIN	Germany	Steel, Sheet, Plate and Strip
10216-5	BS	British	Steel, Sheet, Plate and Strip
X6CrNiMoNb17 12 2	DIN	Germany	Steel, Sheet, Plate and Strip
X6CrNiMoNb17 12 2	UNE	Spain	Steel, Bar, Wire, Rod and Forging
X6CrNiMoNb17 12 2 KKW	ONORM	Australia	Steel
318 S 17	BS	British	Steel and Wire

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.