



## Material - AFNOR NF X6CrNiNb18-10

### Standard Specification for Seamless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - AFNOR NF X6CrNiNb18-10 Seamless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Bar and Rods

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.045 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	17.000 - 19.000		
Nickel	Ni %	9.000 - 12.000		
Niobium	Nb %	0.800 - 1.000		
Iron	Fe %	Balance	<b>Mechanical Properties</b> Tensile Strength in Mpa      510 - 740 Yield Strength in Mpa      205 min. Elongation in %      30 min. Reduction of Area in %      - Hardness in HB      230 max. Impact in Joule      -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4550	EN	European Union	Tube
1.455	DIN	Germany	Steel
1.455	DIN	Germany	Steel
X6CrNiNb18 10	DIN	Germany	Steel and Tube
X6CrNiNb18 10	ISO	International	Steel, Forging and Bar
X6CrNiNb18 10S	ONORM	Australia	Steel
Z8CENb18-10	AFNOR NF	France	Steel

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.