

Material - AFNOR NF Z 1 CN 25-20

Standard Specification for Seemless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - AFNOR NF Z 1 CN 25-20 Seemless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Tube

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|-------------------------------|-----------|
| Carbon | C % | 0.015 max. | Solution Annealing | |
| Silicon | Si % | 0.400 max. | | |
| Manganese | Mn % | 2.000 max. | | |
| Phosphorus | Р% | 0.025 max. | | |
| Sulphur | S % | 0.010 max. | | |
| Chromium | Cr % | 24.000 - 26.000 | | |
| Molybdenum | Mo % | 0.500 max. | | |
| Nickel | Ni % | 19.000 - 22.000 | | |
| Iron | Fe % | Balance | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 480 - 740 |
| - | - | - | Yield Strength in Mpa | 205 min. |
| - | - | - | Elongation in % | 35 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impac <mark>t in Joule</mark> | 60 J @ RT |

| Cross Reference Table | | | | |
|-----------------------|----------|----------------|-------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| 1.4335 | EN | European Union | Tube | |
| 1.4335 | DIN | Germany | Steel | |
| 1.4335 | DIN | Germany | Steel | |
| X1CrNi25 21 | DIN | Germany | Steel, Rolling and Forging | |
| X1CrNi25 21 | UNI | Italy | Steel, Sheet, Strip and Plate | |
| X1CrNi25 21 | AFNOR NF | France | Steel | |
| X1CrNi25-20 | AFNOR NF | France | Steel and Tube | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS