



Material - AFNOR NF Z 4 CND 13.4 M

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - AFNOR NF Z 4 CND 13.4 M Steel Castings for General Engineering Purposes Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.		
Silicon	Si %	0.800 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.000 max.		alizing or Hardoning and
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	12.000 - 13.500		
Nickel	Ni %	3.500 - 4.500		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	700 min.
-	-	-	Yield Strength in Mpa	500 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	210 - 320
-	-	-	Impac <mark>t in Joule</mark>	30 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
425C11	BS	British	Casting	
2074/H3C	AS	Australia	Casting	
2074/H3CM	AS	Australia	Casting	
Z 4 CN 13.4 M	AFNOR NF	France	Casting	
1.4313	EN	European Union	Casting	
X3CrNiMo13-4	EN	European Union	Casting	
1.4313	AFNOR NF	France	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.