



Material - AISI 1008

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets, Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - AISI 1008 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.500 max.		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	260 - 655
			Yield Strength in Mpa	160 min.
			Elongation in %	20 min.
			Reduction of Area in %	45 - 55
			Hardness in HB	86 - 95
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10080	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1008	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 1040 1008	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 108 Grade 1008	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 29 1008	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 29 M1008	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 510 1008	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.