



Material - AISI 1037

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group - Ferrous Mild Steel Alloys

Sub Group - AISI 1037 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Chemical Composition		Heat Treatment	
C %	0.320 - 0.380		
Mn %	0.700 - 1.000	As Raw or Annealing or Normalizing or Hardening and Tempering	
P %	0.040 max.		izing or Hordoning and
S %	0.050 max.		•
В%	0.0005 - 0.003		8
Al %	0.020 max.		
Cu %	0.200 max.		
Nb %	0.015 max.		
Si %	0.100 max.	Mechanical Pro	perties
V %	0.020 max.	Tensile Strength in Mpa	510 - 570
Fe %	Balance	Yield Strength in Mpa	280 min.
-	-	Elongation in %	12 min.
-	-	Reduction of Area in %	35 - 40
-	-	Hardness in HB	143 - 167
-	-	Impact in Joule	-
	C % Mn % P % S % B % Al % Cu % Nb % Si % V % Fe % -	C % 0.320 - 0.380 Mn % 0.700 - 1.000 P % 0.040 max. S % 0.050 max. B % 0.0005 - 0.003 Al % 0.020 max. Cu % 0.200 max. Nb % 0.015 max. Si % 0.100 max. V % 0.020 max. Fe % Balance	C % 0.320 - 0.380 Mn % 0.700 - 1.000 P % 0.040 max. S % 0.050 max. B % 0.0005 - 0.003 Al % 0.020 max. Cu % 0.200 max. Nb % 0.100 max. V % 0.020 max. Fe % Balance Fe % Balance Fe % Belongation in % Reduction of Area in % Hardness in HB

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
G10370	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1037	SAE	USA	Steel	
A 1040 1037	ASTM	USA	Steel	
A 29 1037	ASTM	USA	Steel and Bar	
A 510 1037	ASTM	USA	Wire Rod and Round Wire	
A 576 10L37	ASTM	USA	Steel and Bar	
A 830 1037	ASTM	USA	Plate	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.