

Material - AISI 1126

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE 1126 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.230 - 0.290		
Manganese	Mn %	0.700 - 1.000	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.080 - 1.000		
Lead	Pb %	0.150 - 0.350		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	440 min.
-	-	-	Yield Strength in Mpa	370 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	40 min.
-	-	-	Hardness in HB	126 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G11260	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1126	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
-	-		-		
-	-	-	•		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.