



Material - AISI 1212

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

Group - Ferrous Mild Steel Alloys

Sub Group - AISI 1212 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Chemical Composition		Heat Treatment	
C %	0.130 max.	As Raw or Annealing or Normalizing or Hardening an Tempering	
Mn %	0.700 - 1.000		
Р%	0.070 - 0.120		izing or Hardoning and
S %	0.160 - 0.230		
Al %	0.020 max.		3
Nb %	0.025 max.		
V %	0.020 max.		
Fe %	Balance		
-	-	Mechanical Properties	
-	-	Tensile Strength in Mpa	390 - 540
-	-	Yield Strength in Mpa	230 min.
-	-	Elongation in %	10 min.
-	-	Reduction of Area in %	35 - 45
-	-	Hardness in HB	110 - 255
-	-	Impact in Joule	-
	C % Mn % P % S % Al % Nb % V % Fe %	C % 0.130 max. Mn % 0.700 - 1.000 P % 0.070 - 0.120 S % 0.160 - 0.230 Al % 0.020 max. Nb % 0.025 max. V % 0.020 max. Fe % Balance	C % 0.130 max. Mn % 0.700 - 1.000 P % 0.070 - 0.120 S % 0.160 - 0.230 Al % 0.020 max. Nb % 0.025 max. V % 0.020 max. Fe % Balance - Tensile Strength in Mpa Yield Strength in Mpa Yield Strength in Mpa Elongation in % Reduction of Area in % Hardness in HB

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
G12120	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1212	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
A 1040 1212	ASTM	USA	Steel	
A 576 1212	ASTM	USA	Steel and Bar	
SA-29 1212	ASME	USA	Steel	
A 108 Grade 1212	ASTM	USA	Steel and Bar	
A 29 1212	ASTM	USA	Steel and Bar	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.