



## Material - AISI 1524

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar

**Group - Ferrous Mild Steel Alloys** 

Sub Group - AISI 1524 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel and Bar Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel and Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.190 - 0.250		
Manganese	Mn %	1.350 - 1.650	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.040 max.		olizing or Hordoning and
Sulphur	S %	0.050 max.		· ·
Boron	В%	0.0005 - 0.003		ııg
Aluminium	Al %	0.020 max.		
Copper	Cu %	0.200 max.		
Niobium	Nb %	0.025 max.		
Silicon	Si %	0.100 max.	Mechanical Properties	
Vanadium	V %	0.050 max.	Tensile Strength in Mpa	510 - 570
Iron	Fe %	Balance	Yield Strength in Mpa	280 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	35 - 42
-	-	-	Hardn <mark>ess in HB</mark>	149 - 163
-	-	-	Impa <mark>ct in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G15240	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1524	SAE	USA	Steel		
A 29 1524	ASTM	USA	Steel and Bar		
A 510 1524	ASTM	USA	Wire Rod, Round Wire and Steel		
A 830 G15240	ASTM	USA	Plate and Steel		
A 513 Grade 1524	ASTM	USA	Tubing		
A 519 1524	ASTM	USA	Tubing		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.