

Material - AISI 202

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - AISI 202 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bar, Wire, Shape, Steel and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Solution Annealing	
Silicon	Si %	1.000 max.		
Manganese	Mn %	7.500 - 10.500		
Phosphorus	P %	0.060 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	17.000 - 19.000		
Nickel	Ni %	4.000 - 6000		
Nitrogen	N %	0.250 max.		-
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	515 - 1069
-	-	-	Yield Strength in Mpa	206 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in HB	241 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
A240 UNS S20200	ASTM	USA	Steel, Plate, Sheet and Strip	
202	SAE	USA	USA Bar, Wire, Shape, Steel and Forging	
X12CrMnNiN18-9-5	AFNOR NF	France	Steel	
X12CrMnNiN18-9-5	DIN	Germany	Steel	
X12CrMnNiN18-9-5	UNI	Italy	Steel, Sheet, Strip and Plate	
X12CrMnNiN18 9 5	EN	European Union	Steel	
SUS 202	JIS	Japan	Steel, Plate, Strip and Sheet	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.