



Material - AISI 301

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - AISI 301 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Sheet, Bar and Strip

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|-------------------------|----------|
| Carbon | C % | 0.150 max. | Solution Annealing | |
| Silicon | Si % | 1.000 max. | | |
| Manganese | Mn % | 2.000 max. | | |
| Phosphorus | P % | 0.045 max. | | |
| Sulphur | S % | 0.030 max. | | |
| Chromium | Cr % | 16.000 - 18.000 | | |
| Nickel | Ni % | 6.000 - 8.000 | | |
| Nitrogen | N % | 0.100 max. | | |
| Iron | Fe % | Balance | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| | | | Mechanical Properties | |
| | | | Tensile Strength in Mpa | 515 min. |
| | | | Yield Strength in Mpa | 205 min. |
| | | | Elongation in % | 8 min. |
| | | | Reduction of Area in % | - |
| | | | Hardness in HB | 217 max. |
| | | | Impact in Joule | - |

| Cross Reference Table | | | |
|-----------------------|----------|-----------|-------------------------------|
| Material | Standard | Country | Grade Belong to the Industry |
| A240 UNS S30100 | ASTM | USA | Steel, Plate, Sheet and Strip |
| 301 | SAE | USA | Steel |
| 301 S 21 | BS | British | Steel, Plate, Sheet and Strip |
| STS 301 | KS | Korea | Steel, Plate, Sheet and Strip |
| S30100 | UNS | USA | Steel |
| 301 | AS | Australia | Steel, Plate, Sheet and Strip |
| S30103 | UNS | USA | Steel |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.