



Material - AISI 410

Standard Specification for Stainless and Heat Resisting Steels Bar, Wire, Shapes and Forging

Group - Ferrous Stainless Steel Alloys

Sub Group - AISI 410 Stainless and Heat Resisting Steels Bar, Wire, Shapes and Forging Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bar, Wire, Shapes and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 - 0.150		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	Р%	0.040 max.	Annealing or Hardening + Tempering	
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.500 - 13.500		
Iron	Fe %	Balance		
-	-	-		
-	/-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	415 - 1402.7
-	-	-	Yield Strength in Mpa	205 min.
-	-	-	Elongation in %	11 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardn <mark>ess in HB</mark>	143 - 331
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
5351	AMS	USA	Casting	
410 C 21	BS	British	Casting	
15ch13L	GOST	Russia	Casting	
385 G X 12 Cr 13	SFS	Finland	Casting	
A217 CA 15	ASTM	USA	Casting	
A487 CA 15	ASTM	USA	Casting	
A743 CA 15	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.