



Material - AISI 4130

Standard Specification for Structural and Construction Steels

Group - Ferrous Mild Steel Alloys

Sub Group - AISI 4130 Structural and Construction Steels

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Forging, Bar, Wire and Shape

Chemical Composition			Heat Treatment	
Carbon	C %	0.280 - 0.330	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.160 - 0.250		
Manganese	Mn %	0.400 - 0.600		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.026 max.		
Chromium	Cr %	0.800 - 1.100		
Nickel	Ni %	0.250 max.		
Molybdenum	Mo %	0.150 - 0.250		
Copper	Cu %	0.350 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	480 - 1379
-	-	-	Yield Strength in Mpa	345 min.
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	20 min.
-	-	-	Hardness in HRC	25 max.
-	-	-	Impact in Joule	79.1 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J13045	UNS	USA	Casting
4130	SAE	USA	Bar, Tube, Sheet, Strip and Forging
A579 Grade 13	ASTM	USA	Forging
J13048	UNS	USA	Casting
K13247	UNS	USA	Steel
AMS 4130	AMS	USA	Bar and Forging
A732 7Q	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.