



Material - AISI 6120

Standard Specification for Structural and Constructional Steels Forging, Bar, Wire and Shape

Group - Ferrous Mild Steel Alloys

Sub Group - AISI 6120 Structural and Constructional Steels Forging, Bar, Wire and Shape

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Forging, Bar, Wire and Shape

Chemical Composition			Heat Treatment	
Carbon	C %	0.170 - 0.220	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.150 - 0.350		
Manganese	Mn %	0.700 - 0.900		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	0.700 - 0.900		
Vanadium	V %	0.100 min.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	586 min.
-	-	-	Yield Strength in Mpa	379 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	13.3 - 22 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J13052	UNS	USA	Casting
200-400 W	JIS	Japan	Casting
B 2	BS	British	Forging
B 4	BS	British	Forging
B 5	BS	British	Forging
B 6	BS	British	Forging
A732 5N	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.