



Material - AMS 6150

Standard Specification for Structural and Constructional Steels

Group - Ferrous Mild Steel Alloys

Sub Group - AMS 6150 Structural and Constructional Steels

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.480 - 0.530	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.150 - 0.350		
Manganese	Mn %	0.700 - 0.900		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	0.800 - 1.1000		
Vanadium	V %	0.150 min.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	1310 min.
			Yield Strength in Mpa	1172 min.
			Elongation in %	4 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
J15048	UNS	USA	Casting
6150	SAE	USA	Bar, Tube, Sheet, Strip and Forging
6150	AISI	USA	Forging, Bar, Wire, and Shape
A732 12Q	AISI	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.