



## Material - AMS 6386 Type 12

Standard Specification for Sheet and Plate-Heat Low Alloy

**Group - Ferrous Mild Steel Alloys** 

Sub Group - AMS 6386 Type 12 Sheet and Plate-Heat Low Alloy

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Steel** 

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 - 0.200		
Silicon	Si %	0.150 - 0.350		
Manganese	Mn %	0.600 - 1.000		
Phosphorus	P %	0.035 max.	Annealing or Normalising or Hardening + Tempering	Hardening + Tempering
Sulphur	S %	0.040 max.		
Chromium	Cr %	0.400 - 0.650		
Nickel	Ni %	0.700 - 1.000		
Molybdenum	Mo %	0.400 - 0.600		
Copper	Cu %	0.150 - 0.500	Mechanical Properties	
Vanadium	V %	0.030 - 0.080	Tensile Strength in Mpa	758 - 896
Boron	В %	0.0005 - 0.005	Yield Strength in Mpa	689 min.
Iron	Fe %	Balance	Elongation in %	18 min.
-	-	-	Reduction of Area in %	30 min.
-	-	-	Hardness in HB	235 - 293
-	-	-	Impact in Joule	13 J @ RT

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
1.8719	DIN	Germany	Steel		
1.892	EN	European Union	Steel		
J12084	UNS	USA	Casting		
K11576	UNS	USA	Casting		
SA-487 Grade 7A	ASME	USA	Casting		
SA-592 Grade F	ASME	USA	Forging		
A487 7A	ASTM	USA	Casting		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.