



Material - AS 2074/L1B

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - AS 2074/L1B Steel Castings for General Engineering Purposes
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 - 0.330		
Silicon	Si %	0.600 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.200 - 1.600		alizing or Hardoning and
Phosphorus	P %	0.050 max.		ŭ
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		_
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	620 min.
-	-	-	Yield Strength in Mpa	370 min.
-	-	-	Elongation in %	11 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	179 - 229
-	-	-	Impac <mark>t in Joule</mark>	20 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A5	BS	British	Casting	
A6	BS	British	Casting	
2708 Grade 2	IS	India	Casting	
2708 Grade 3	IS	India	Casting	
1527	SAE	USA	Casting	
1527	AISI	USA	Bar	
A 830 1527	ASTM	USA	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.