



Material - AS 2074/L5H

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - AS 2074/L5H Steel Castings for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 - 0.150		
Silicon	Si %	0.450 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.400 - 0.700		alizing or Hardoning and
Phosphorus	P %	0.030 max.		· ·
Sulphur	S %	0.030 max.		
Chromium	Cr %	0.300 - 0.500		
Molybdenum	Mo %	0.400 - 0.600		
Nickel	Ni %	0.300 max.		•
Copper	Cu %	0.300 max.	Mechanical Properties	
Tin	Sn %	0.050 max.	Tensile Strength in Mpa	510 min.
Vanadium	V %	0.220 - 0.350	Yield Strength in Mpa	295 min.
Iron	Fe %	Balance	Elongation in %	17 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
В7	BS	British	Casting	
660	BS	British	Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.