



Material - AS 409

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - AS 490 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel, Sheet, Plate and Strip

Chemical Composition			Heat Treatment			
Carbon	C %	0.080 max.	Annealing or Hardening + Tempering			
Silicon	Si %	1.000 max.				
Manganese	Mn %	1.000 max.				
Phosphorus	P %	0.045 max.				
Sulphur	S %	0.030 max.				
Chromium	Cr %	10.500 - 11.750				
Molybdenum	Mo %	0.350 max.				
Nickel	Ni %	0.500 max.				
Titanium	Ti %	0.750 max.				
Copper	Cu %	0.350 max.				
Iron	Fe %	Balance	<th colspan="2">Mechanical Properties</th>		Mechanical Properties	
-	-	-	Tensile Strength in Mpa	380 min.		
-	-	-	Yield Strength in Mpa	205 min.		
-	-	-	Elongation in %	20 min.		
-	-	-	Reduction of Area in %	-		
-	-	-	Hardness in HB	80 min.		
-	-	-	Impact in Joule	-		

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A240 UNS S40900	ASTM	USA	Steel, Plate, Sheet and Strip	
S409000	UNS	USA	Steel	
409	SAE	USA	Steel	
STS 409LTP	KS	Korea	Steel and Pipe	
SUH 409	JIS	Japan	Steel, Plate and Sheet	
409 S 19	BS	British	Steel, Sheet, Plate and Strip	
SA-240 UNS S40900	ASME	USA	Steel	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.