



Material - AS 8625

Standard Specification for Alloy Steel Casting

Group - Ferrous Mild Steel Alloys

Sub Group - AS 8625 Alloy Steel Casting, Bar, Wire, Tube and Forging

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar, Wire, Tube and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.220 - 0.290		
Silicon	Si %	0.150 - 0.350	As- Cast or Normalising or Annealing or Hardening + Tempering	
Manganese	Mn %	0.600 - 0.900		nooling or Hardoning I
Phosphorus	P %	0.035 max.		· ·
Sulphur	S %	0.040 max.		
Chromium	Cr %	0.350 - 0.600		
Molybdenum	Mo %	0.150 - 0.250		
Nickel	Ni %	0.400 - 0.700		
Copper	Cu %	0.350 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in BH</mark> N	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
A915 Grade SC 8625	UNS	USA	Casting	
J12595	UNS	USA	Bar, Wire, Tube and Forging	
A 29 8625	ASTM	USA	Bar, Wire, Tube and Forging	
A 505 8625	ASTM	USA	Bar, Wire, Tube and Forging	
8625	AISI	USA	Bar, Wire, Tube and Forging	
8625	SAE	USA	Bar, Wire, Tube and Forging	
8625	AMS	USA	Bar, Wire, Tube and Forging	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.