



Material - AS C450L0

Standard Specification for Structural Steel Hollow Sections

Group - Ferrous Mild Steel Alloys

Sub Group - AS C450L0 Structural Steel Hollow Sections

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 max.	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.250 max.		
Manganese	Mn %	1.700 max.		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	0.300 max.		
Nickel	Ni %	0.250 max.		
Molybdenum	Mo %	0.350 max.		
Vanadium	V %	0.100 max.		
Aluminium	Al %	0.100 max.		
Copper	Cu %	0.150 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	500 min.
-	-	-	Yield Strength in Mpa	450 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	18 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.8830	EN	European Union	Steel
1.8866	DIN	Germany	Steel
4020	AISI	USA	Forging, Bar, Wire, and Shape
P355Q	AFNOR NF	France	Steel
P355QH	UNI	Italy	Steel
C450	AS	Australia	Steel
A732 6N	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.