GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-182 Grade F 9

Standard Specification for Forged or Rolled Alloy and Stainless Steel Pipe Flanges, Forged Fittings and Valves and Parts for High-Temperature Service

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-182 Grade F 9 Forged or Rolled Alloy and Stainless Steel Pipe Flanges, Forged Fittings and Valves and Parts for High-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe and Forging

Chemical Composition		
Carbon	C %	0.150 max.
Manganese	Mn %	0.300 - 0.600
Phosphorus	P %	0.030 Max.
Sulphur	S %	0.030 Max.
Silicon	Si %	0.500 - 1.000
Chromium	Cr %	8.000 - 10.000
Molybdenum	Mo %	0.900 - 1.100
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing or Normalising & Tempering

Mechanical Properties	
Tensile Strength in Mpa	585 min.
Yield Strength in Mpa	380 min.
Elongation in %	20 min.
Reduction of Area in %	40 min.
Hardness in BHN	179 - 217
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
K90941	UNS	USA	Steel
17176 12 CrMo 9 1	DIN	Germany	Steel and Tubing
17176 1.7386	DIN	Germany	Steel and Tubing
3203 SFVA F 9	JIS	Japan	Steel
A 182 Grade F 9	ASTM	USA	Steel and Pipe
A 336 Grade F 9	ASTM	USA	Steel and Forging
A 989 K90941	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.