GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-240 S32101

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate,Sheet and Srtip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-240 S32101 Chromium and Chromium-Nickel Stainless Steel Plate,Sheet and Srtip for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition		
Carbon	C %	0.040 max.
Manganese	Mn %	4.000 - 6.000
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	21.000 - 22.000
Nickel	Ni %	1.350 - 1.700
Molybdenum	Mo %	0.100 - 0.800
Nitrogen	N %	0.200 - 0.250
Copper	Cu %	0.100 - 0.800
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw

Mechanical Properties	
Tensile Strength in Mpa	700 min.
Yield Strength in Mpa	530 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in BHN	290 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
SA-276 S32101	ASME	USA	Steel, Bar and Shapes
SA-182 S32101	ASME	USA	Steel and Pipe
A276 S32101	ASTM	USA	Steel, Bar and Shapes
A 240 UNS S32101	ASTM	USA	Plate, Sheet and Strip
A 815 S32101	ASTM	USA	Steel and Pipe
A 182 S32101	ASTM	USA	Steel and Pipe
A 182 F 69	ASTM	USA	Steel and Pipe

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.