GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-240 S32803

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate,Sheet and Srtip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-240 S32803 Chromium and Chromium-Nickel Stainless Steel Plate,Sheet and Srtip for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition		
Carbon	C %	0.015 max.
Manganese	Mn %	0.500 max.
Phosphorus	P %	0.020 max.
Sulphur	S %	0.0035 max.
Silicon	Si %	0.550 max.
Chromium	Cr %	28.000 - 29.000
Nickel	Ni %	3.000 - 4.000
Molybdenum	Mo %	1.800 - 2.500
Nitrogen	N %	0.020 max.
Niobium	Nb %	0.024 - 0.500
C + N	C % + N %	0.030 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw

Mechanical Properties	
Tensile Strength in Mpa	600 min.
Yield Strength in Mpa	500 min.
Elongation in %	16 min.
Reduction of Area in %	-
Hardness in BHN	241 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
SA-268 28-2-3.5	ASME	USA	Steel and Tubing
SA-268 S32803	ASME	USA	Steel and Tubing
A 240 S32803	ASTM	USA	Plate, Sheet and Strip
A 176 S32803	ASTM	USA	Sheet, Plate and Strip
A 959 S32803	ASTM	USA	Steel
A 268 28-2-3.5	ASTM	USA	Steel and Tubing
A 268 S32803	ASTM	USA	Steel and Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.