GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-240 Type 301L

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate,Sheet and Srtip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-240 Type 301L Chromium and Chromium-Nickel Stainless Steel Plate,Sheet and Srtip for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition		
Carbon	C %	0.030 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	16.000 - 18.000
Nickel	Ni %	6.000 - 8.000
Nitrogen	N %	0.200 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw

Mechanical Properties	
Tensile Strength in Mpa	550 min.
Yield Strength in Mpa	220 min.
Elongation in %	45 min.
Reduction of Area in %	-
Hardness in BHN	241 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S30103	UNS	USA	Steel
A 240 Type 301L	ASTM	USA	Plate, Sheet,and Strip
A 959 Type 301LN	ASTM	USA	Steel
A 240 Type 301LN	ASTM	USA	Plate, Sheet,and Strip
D 3698 STS 301L	KS	Korea	Plate, Sheet,and Strip
G 4305 SUS 301L	JIS	Japan	Plate, Sheet,and Strip
G 4304 SUS 301L	JIS	Japan	Plate, Sheet,and Strip

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.