GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-240 Type 310MoLN

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate,Sheet and Srtip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-240 Type 310MoLN Chromium and Chromium-Nickel Stainless Steel Plate,Sheet and Srtip for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition		
Carbon	C %	0.020 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.030 max.
Sulphur	S %	0.010 max.
Silicon	Si %	0.500 max.
Chromium	Cr %	24.000 - 26.000
Nickel	Ni %	20.500 - 23.500
Molybdenum	Mo %	1.600 - 2.600
Nitrogen	N %	0.090 - 0.150
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw

Mechanical Properties	
Tensile Strength in Mpa	580 min.
Yield Strength in Mpa	270 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in BHN	217 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
SA-312 UNS S31050	ASME	USA	Steel and Pipe
A 959 Type 310MoLN	ASTM	USA	Steel
A 213 S31050	ASTM	USA	Steel and Tubing
A 312 S31050	ASTM	USA	Steel and Pipe
A 943 S31050	ASTM	USA	Steel and Pipe
A 249 S31050	ASTM	USA	Steel and Tubing
A 182 F 310MoLN	ASTM	USA	Pipe and Forging

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.