GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-240 Type 316H

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate,Sheet and Srtip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-240 Type 316H Chromium and Chromium-Nickel Stainless Steel Plate,Sheet and Srtip for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Plate, Sheet and Strip

Chemical Composition		
Carbon	C %	0.040 - 0.100
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Silicon	Si %	0.750 max.
Chromium	Cr %	16.000 - 18.000
Nickel	Ni %	10.000 - 14.000
Molybdenum	Mo %	2.000 - 3.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw

Mechanical Properties	
Tensile Strength in Mpa	515 min.
Yield Strength in Mpa	205 min.
Elongation in %	40 min.
Reduction of Area in %	-
Hardness in BHN	217 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
J 405 316H	SAE	USA	Steel
D 3576 STS 316 HTP	KS	Korea	Steel and Pipe
G 3459 SUS 316 HTP	JIS	Japan	Steel and Pipe
G 3463 SUS 316 HTB	JIS	Japan	Steel and Tubing
SA-213 Grade TP 316H	ASME	USA	Steel and Tubing
A 213 TP316H	ASTM	USA	Steel and Tubing
A 943 TP316N	ASTM	USA	Steel and Pipe

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.