

## Material - ASME SA-240 UNS S40900

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

**Group - Ferrous Stainless Steel Alloys** 

Sub Group - ASME SA-240 UNS S40900 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.	Annealing or Hardening + Tempering	
Sulphur	S %	0.020 max.		
Chromium	Cr %	10.500 - 11.700		
Nickel	Ni %	0.500 max.		
Nitrogen	N %	0.030 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	380 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	179 max.
-	-		Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A240 UNS S40900	ASTM	USA	Steel, Plate, Sheet and Strip		
S409000	UNS	USA	Steel		
409	AS	Australia	Steel, Sheet, Plate and Strip		
409	SAE	USA	Steel		
STS 409LTP	KS	Korea	Steel and Pipe		
SUH 409	JIS	Japan	Steel, Plate and Sheet		
409 S 19	BS	British	Steel, Sheet, Plate and Strip		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.