GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-268 TP410

Standard Specification for Seamless and Welded Ferritic and Martensitic Stainless Steel Tubing for General Service

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-268 TP410 Seamless and Welded Ferritic and Martensitic Stainless Steel Tubing for General Service

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Tubing

Chemical Composition		
Carbon	C %	0.150 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max
Silicon	Si %	1.000 max.
Chromium	Cr %	11.500 - 13.500
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalizing or Tempering or As-Raw

Mechanical Properties	
Tensile Strength in Mpa	415 min.
Yield Strength in Mpa	205 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in BHN	207 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S41000	UNS	USA	Steel
S41008	UNS	USA	Steel
SA-240 Type 410	ASME	USA	Plate, Sheet and Strip
G 4312 SUS 410	JIS	Japan	Steel, Plate and Sheet
A 959 Type 410	ASTM	USA	Steel
A 959 410S	ASTM	USA	Steel
A 988 S41000	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.