GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-276 S32101

Standard Specification for Stainless Steel Bars and Shapes

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-276 S32101 Stainless Steel Bars and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bars and Shapes

Chemical Composition		
Carbon	C %	0.040 max.
Manganese	Mn %	4.000 - 6.000
Phosphorus	P %	0.040 Max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	21.000 - 22.000
Nickel	Ni %	1.350 - 1.700
Molybdenum	Mo %	0.100 - 0.800
Nitrogen	N %	0.200 - 0.250
Copper	Cu %	0.100 - 0.800
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Annealing

Mechanical Properties	
Tensile Strength in Mpa	650 min.
Yield Strength in Mpa	450 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in BHN	290 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S321010	UNS	USA	Steel
SA-240 S32101	ASME	USA	Plate, Sheet and Strip
A276 S32101	ASTM	USA	Steel, Bar and Shapes
A 240 UNS S32101	ASTM	USA	Plate, Sheet and Strip
A 815 S32101	ASTM	USA	Steel and Pipe
A 182 S32101	ASTM	USA	Steel and Pipe
A 182 F 69	ASTM	USA	Steel and Pipe

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.