GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-276 S32550

Standard Specification for Stainless Steel Bars and Shapes

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-276 S32550 Stainless Steel Bars and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bars and Shapes

Chemical Composition		
Carbon	C %	0.040 max.
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	24.000 - 27.000
Nickel	Ni %	4.500 - 6.500
Molybdenum	Mo %	2.900 - 3.900
Nitrogen	N %	0.100 - 0.250
Copper	Cu %	1.500 - 2.500
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Strain Hardening

Mechanical Properties	
Tensile Strength in Mpa	860 min.
Yield Strength in Mpa	720 min.
Elongation in %	16 min.
Reduction of Area in %	-
Hardness in BHN	335 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
A 959 Type 255	ASTM	USA	Steel
A 240 S32550	ASTM	USA	Plate, Sheet and Strip
A 276 S32550	ASTM	USA	Bars and Shapes
A 928 S32550	ASTM	USA	Steel and Pipe
A 790 S32550	ASTM	USA	Steel and Pipe
A 815 S32550	ASTM	USA	Steel and Pipe
A 789 S32550	ASTM	USA	Steel and Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.