GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-276 S32760

Standard Specification for Stainless Steel Bars and Shapes

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-276 S32760 Stainless Steel Bars and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bars and Shapes

Chemical Composition		
Carbon	C %	0.030 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.030 max.
Sulphur	S %	0.010 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	24.000 - 26.000
Nickel	Ni %	6.000 - 8.000
Molybdenum	Mo %	3.000 - 4.000
Nitrogen	N %	0.200 - 0.300
Copper	Cu %	0.500 - 1.000
Tungsten	W %	0.500 - 1.000
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-

Heat Treatment
Strain Hardening

Mechanical Properties	
Tensile Strength in Mpa	860 min.
Yield Strength in Mpa	720 min.
Elongation in %	16 min.
Reduction of Area in %	-
Hardness in BHN	335 max.
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
A 240 S32760	ASTM	USA	Plate, Sheet and Strip
A 182 F 55	ASTM	USA	Steel and Pipe
A 276 S32760	ASTM	USA	Bar and Shapes
A 789 S32760	ASTM	USA	Steel and Tubing
A 790 S32760	ASTM	USA	Steel and Pipe
A 815 S32760	ASTM	USA	Steel and Pipe
A 988 S32760	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.