GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-276 Type 302

Standard Specification for Stainless Steel Bars and Shapes

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-276 Type 302 Stainless Steel Bars and Shapes

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Bars and Shapes

Chemical Composition		
Carbon	C %	0.150 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Silicon	Si %	1.000 max.
Chromium	Cr %	17.000 - 19.000
Nickel	Ni %	8.000 - 10.000
Nitrogen	N %	0.100 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw

Mechanical Properties	
Tensile Strength in Mpa	860 min.
Yield Strength in Mpa	690 min.
Elongation in %	12 min.
Reduction of Area in %	35 min.
Hardness in BHN	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
S30200	UNS	USA	Steel
A 368 Type 302	ASTM	USA	Steel and Wire
A 492 Type 302	ASTM	USA	Steel and Wire
A 313 Type 302	ASTM	USA	Steel and Wire
A 478 Type 302	ASTM	USA	Steel and Wire
A 314 302	ASTM	USA	Steel and Bars
A 276 302	ASTM	USA	Bars and Shapes

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.