



Material - ASME SA-29 1215

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group - Ferrous Mild Steel Alloys

Sub Group - ASTM A 576 1215 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.090 max.	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.750 - 1.050		
Phosphorus	P %	0.040 - 0.090		alizing or Hardoning and
Sulphur	S %	0.260 - 0.350		· ·
Iron	Fe %	Balance		iiig
-	-	-		
-	-	-		
-	-	-		
-	/ -	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in HB</mark>	110 - 255
-	-	-	Impa <mark>ct in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country Grade Belong to the Industry			
G12150	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1215	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1215	AISI	USA	Steel and Bar		
A 1040 1215	ASTM	USA	Steel		
A 576 1215	ASTM	USA	Steel and Bar		
A 108 Grade 1215	ASTM	USA	Steel and Bar		
A 29 1215	ASTM	USA	Steel and Bar		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.