



**GRAVITY CAST PVT. LTD.**  
**GRAVITY GROUP OF COMPANIES**

## Material - ASME SA-29 Grade 1008

Standard Specification for Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished,  
General Requirements For

Group - Ferrous Mild Steel Alloys

Sub Group - ASME SA-29 Grade 1008 Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General  
Requirements For

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel and Bars

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Raw or Annealing or Normalizing or Hardening + Tempering	
Manganese	Mn %	0.300 - 0.500		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	-
-	-	-	Impact in Joule	-

[www.gravitycastindia.com](http://www.gravitycastindia.com)

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10080	UNS	USA	Shapes, Plates, Strip, Sheets and Tubing
J 467 M1008	SAE	USA	Steel
SAE J 403 1008	AISI	USA	Shapes, Plates, Strip, Sheets and Tubing
10016-4 C 8 D 2	EN	European Union	Steel and Rods
A 510 1008	ASTM	USA	Steel and Wire Rods
A 576 1008	ASTM	USA	Steel and Bars
A 108 Grade 1008	ASTM	USA	Steel and Bars

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

**ONE STOP SOLUTION FOR METAL PARTS**