

## **Material - ASME SA-29 Grade 1011**

Standard Specification for Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General Requirements For

**Group - Ferrous Mild Steel Alloys** 

Sub Group - ASME SA-29 Grade 1011 Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General Requirements For

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Steel and Bars

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 - 0.130		
Manganese	Mn %	0.600 - 0.900	As-Raw or Annealing or Normalizing or Hardening - Tempering	
Phosphorus	P %	0.040 max.		malizing or Hardoning I
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		ilig
-	-			
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	7-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	-
-	-	-	Impact in Joule	-

## www.gravitycastindia.com

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G10110	UNS	USA	Steel		
G10111	UNS	USA	Steel, Bars and Forging		
G10114	UNS	USA	Steel, Bars and Forging		
SAE J 403 1011	AISI	USA	Steel, Bars, Forging, Rods and Tubing		
A 29 1011	ASTM	USA	Steel and Bars		
A 512 1011	ASTM	USA	Steel and Tubing		
A 510 1011	ASTM	USA	Steel and Wire Rods		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.