

Material - ASME SA-29 Grade 1035

Standard Specification for Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General Requirements For

Group - Ferrous Mild Steel Alloys

Sub Group - ASME SA-29 Grade 1035 Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General Requirements For

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Steel and Bars

Chemical Composition			Heat Treatment	
Carbon	C %	0.320 - 0.380		
Manganese	Mn %	0.600 - 0.900	As-Raw or Annealing or Normalizing or Hardening Tempering	
Phosphorus	P %	0.040 max.		malizing or Hardoning I
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		IIIB
-	-			
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	-
-	-	-	Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G10350	UNS	USA	Shapes, Plates, Strip, Sheets and Tubing		
AMS 5080 1035	SAE	USA	Steel, Bars, Forging, and Tubing		
SAE J 403 1035	AISI	USA	Shapes, Plates, Strip, Sheets and Tubing		
17200 C 35	DIN	Germany	Steel		
683-18 C 35 E4	ISO	International	Steel		
A 513 1035	ASTM	USA	Steel and Tubing		
A 108 1035	ASTM	USA	Steel and Bars		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.