

Material - ASME SA-29 Grade 1037

Standard Specification for Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General Requirements For

Group - Ferrous Mild Steel Alloys

Sub Group - ASME SA-29 Grade 1037 Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General Requirements For

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Steel and Bars

Chemical Composition			Heat Treatment	
Carbon	C %	0.320 - 0.380		
Manganese	Mn %	0.700 - 1.000	As-Raw or Annealing or Normalizing or Hardening Tempering	
Phosphorus	P %	0.040 max.		malizing or Hardoning I
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		IIIB
-	-			
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	-
-	-	-	Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G10370	UNS	USA	Shapes, Plates, Strip, Sheets and Tubing		
J 1249 1037	SAE	USA	Steel		
1037	AISI	USA	Steel		
17204 36 Mn 4	DIN	Germany	Steel and Tubing		
17204 1.0561	DIN	Germany	Steel and Tubing		
A 510 1037	ASTM	USA	Steel and Wire Rods		
A 576 1037	ASTM	USA	Steel and Bars		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.