

Material - ASME SA-29 Grade 50B46

Standard Specification for Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General Requirements For

Group - Ferrous Mild Steel Alloys

Sub Group - ASME SA-29 Grade 50B46 Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General Requirements For

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Steel and Bars

Chemical Composition			Heat Treatment	
Carbon	C %	0.440 - 0.490		
Manganese	Mn %	0.750 - 1.000	As-Raw or Annealing or Normalizing or Hardening + Tempering	
Phosphorus	P %	0.035 max.		nalizing or Hardoning I
Sulphur	S %	0.040 max.		•
Silicon	Si %	0.150 - 0.350		IIIB
Chromium	Cr %	0.200 - 0.350		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	-
-	-	-	Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G50461	UNS	USA	Steel and Bars		
50B46	AISI	USA	Steel		
50B46 H	AISI	USA	Steel		
A 29 50B46	ASTM	USA	Steel and Bars		
A 519 50B46	ASTM	USA	Steel and Tubing		
A 752 Grade 50B46	ASTM	USA	Wire and Wire Rods		
A 322 50B46	ASTM	USA	Steel and Bars		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.