GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-29 Grade M1044

Standard Specification for Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General Requirements For

Group - Ferrous Mild Steel Alloys

Sub Group - ASME SA-29 Grade M1044 Steel Bars, Carbon and Alloy, Hot-Wrought and Cold-Finished, General Requirements For

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Steel and Bars

Chemical Composition		
Carbon	C %	0.400 - 0.500
Manganese	Mn %	0.250 - 0.600
Phosphorus	P %	0.040 max.
Sulphur	S %	0.050 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing or Normalizing or Hardening + Tempering

Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
G10440	UNS	USA	Forging and Bars
J 467 M1044	SAE	USA	Steel
M1044	AISI	USA	Steel
A 29 M1044	ASTM	USA	Steel and Bars
A 575 M1044	ASTM	USA	Steel and Bars
A 510 1044	ASTM	USA	Steel and Wire Rods
A 513 1044	ASTM	USA	Steel and Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.