



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-351 Grade CH8

Standard Specification for Austenitic and Austenitic-Ferritic Steel Castings for Valves, Flanges and Fittings

Group - Ferrous Stainless Steel Alloys

Sub Group - ASME SA-351 Grade CH8 Austenitic and Austenitic-Ferritic Steel Castings for Valves, Flanges and Fittings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.	Solution Annealing	
Silicon	Si %	1.500 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.400 max.		
Sulphur	S %	0.400 max.		
Chromium	Cr %	22.000 - 26.000		
Nickel	Ni %	12.000 - 15.000		
Molybdenum	Mo %	0.500 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 min.
-	-	-	Yield Strength in Mpa	195 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
309S	AISI	USA	Bar, Wire, Strip, Plat, Sheet and Forging
X 7 CrNi 23-14	DIN	Germany	Rolled and Forged Steel
X 12 CrNi 23-13	EN	European Union	Bar, Wire, Strip, Plat, Sheet and Forging
X 15 CrNi 24-13	AFNOR NF	France	Rolled Tubes for Pressure Service
SUS 309S	JIS	Japan	Wire, Rods for Wedding Material
X 6 CrNi 23-14	UNI	Italy	Plate, Sheet, Strip and Coil
A351 CH8	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS