GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - ASME SA-352 Grade LCC

Standard Specification for Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

Group - Ferrous Mild Steel Alloys

Sub Group - ASME SA-352 Grade LCC Steel Castings, Ferritic and Martensitic, for Pressure-Containing Parts, Suitable for Low-Temperature Service

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Castings

Chemical Composition		
Carbon	C %	0.250 max.
Silicon	Si %	0.600 max.
Manganese	Mn %	1.200 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.045 max.
Nickel	Ni %	0.500 max.
Chromium	Cr %	0.500 max.
Molybdenum	Mo %	0.200 max.
Vanadium	V %	0.030 max.
Vanadium	V %	0.030 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Normalising & Tempering or Hardening & Tempering

Mechanical Properties	
Tensile Strength in Mpa	485 - 655
Yield Strength in Mpa	275 min.
Elongation in %	22 min.
Reduction of Area in %	35 min.
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
J02505	UNS	USA	Steel
EN 10213-2 GP 280 GH	UNI	Italy	Steel
EN 10213-2 GP 240 GR	UNI	Italy	Steel
SA-352 LCB	ASME	USA	Steel
A 352 Grade LCC	ASTM	USA	Steel
A 216 Grade LCB	ASTM	USA	Steel
A 216 Grade LCC	ASTM	USA	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.